

Lynn River

Powder Free Latex



Product Information

Product Code	63052
Material	Latex
Colour	White
Type	Polymer Coated
Interior	Powder-free
Exterior	Full Textured
Sizes	XS-XL
Country of Origin	Malaysia
Storage	Stored in a cool dry place avoiding exposure to direct sunlight, high temperature and humidity.

Features Ambidextrous

AQL	1.5
Glove Weight	6g+/-0.3g(medium)
Glove Length(mm)	Min. 240
Glove width(mm)	Min. 90
Glove Thickness(mm)	0.08(Cuff) 0.10(Palm) 0.12(Finger)

Packaging and Ordering Information

Code	Size	Purchase Unit	Carton Dimensions
63052-XS	XS		
63052-S	S		
63052-M	M	100PCS/BOX 1000PCS/CTN	L340*W260*H235
63052-L	L		
63052-XL	XL		



Quality Standards

FDA Status	Activate Registration number: 3009538921
Audit Standards	ISO 9001 & ISO 13485
Test Standards	EN 374-4: 2013 EN ISO 374-1:2016

Resistance Of Gloves to Permeation By Chemicals

Chemical	EN ISO 374-1:2016 PERFORMANCE LEVEL	EN 374-4:2013 MEAN DEGRADATION / %
Sodium Hydroxide (K) 40%	6	-14.9%
Formaldehyde (T) 37%	1	-22.4%
Sodium Hypochlorite 10-13%	1	52.8%
Hydrogen Peroxide (P) 30%	2	-15.6%

EN ISO 374-1:2016 - permeation levels are based on breakthrough times as follows:

Performance Level	1	2	3	4	5	6
Minimum Breakthrough Time (Min)>	10	>30	>60	>120	>240	>480

Safety gloves to protect against chemicals are classified according to their permeation time (time taken for the chemical to penetrate the glove) and number of chemicals tested:

- Type A - at least 30min each for at least 6 test chemicals
- Type B - at least 30min each for at least 3 test chemicals
- Type C - at least 10min each for at least 1 test chemicals

EN 374-4:2013 - Degradation results indicate the change in puncture resistance of the gloves after exposure to the challenge chemical

EN ISO 374-5:2016 - Resistance to Bacteria and Fungi = Pass, Resistance to Virus = Pass