

Lynn River

Powder Free Latex



Product Information

Product Code	63050
Material	Latex
Colour	Natural (white)
Type	Non-sterile Powdered Latex Examination Gloves
Exterior	Halogenation, silicization and Extensive Washing in water. Donning powder used.
Sizes	XS-XL
Country of Origin	Vietnam
Storage	Store in a dry, ventilated area. Avoid direct sunlight, fluorescent lighting, and storage to photocopy equipments, heat, and moisture. Do not store above 100F (38 C) as this will lead to accelerated aging. Long-term storage can result in pleats, stickiness, and early aging of the gloves.
Features	Powder makes the gloves easier to don and remove. This powder can also help to limit and absorb perspiration, making the gloves more comfortable to wear, especially for extended periods of time. Latex gloves are elastic and resistant to tearing, whilst also offering protection against a range of hazards. Latex gloves are also more easily biodegradable.



AQL	Major defects : AQL 1.5 , Minor defects : AQL 4.0
Glove Weight	XS: 4.2g, S: 4.6g, M: 5.0g, L: 5.4g, XL: 5.8g (+/-0.2g)
Glove Length(mm)	Min. 240
Glove width(mm)	Min. 90
Glove Thickness(mm)	Finger : 0.10 mm, Palm : 0.08 mm, Cuff : 0.06 mm (+/-0.02 mm)

	Before Aging	After Aging
Tensile Strength	Min 18 MPa	Min 14 MPa
Ultimate Elongation	Min 650%	Min 500%

Packaging and Ordering Information

Code	Size	Purchase Unit	Carton Dimensions
63052-XS	XS	100PCS/BOX 1000PCS/CTN	L340*W260*H235
63052-S	S		
63052-M	M		
63052-L	L		
63052-XL	XL		

Quality Standards

FDA Status Using FDA approved absorbable corn starch, USP grade.

Audit Standards ISO 9001, ISO 13485, Compliance with C-TPAT

Test Standards
ASTM
EN 1186-8:2002
EN 1186-9:2002

Type of Stimulant	Testing Condition	Surface Area(dm ²)	Volume of Extractant (ml)	Overall Migration (mg/dm ²)	Commission Regulation (EU) No 10/2011 Requirement for Overall Migration Content (mg/dm ²)
10% Ethanol	40 °C, 2 Hours	4.82	240	1.8	<10
3% Acetic Acid	40 °C, 2 Hours	4.87	240	9.9	<10
20% Ethanol	40 °C, 2 Hours	4.90	240	2.1	<10
50% Ethanol	40 °C, 2 Hours	4.98	240	5.8	<10
Vegatable Oil	40 °C, 2 Hours	4.86	240	<1.0	<10