



### PRODUCT INFORMATION

DuPont™ Tyvek® 400 Dual. Hooded coverall. Tyvek® at the front and large breathable SMS back. Stitched external seams. Elasticated wrists, ankles and face. Elasticated waist (stitched-in). Tyvek® zipper and flap. White.

### ATTRIBUTES

<b>Full Part Number</b>	TDCHF5SWH00
<b>Fabric/Materials</b>	Tyvek® 500 / SMS
<b>Design</b>	Hooded coverall with elastics, Tyvek® front, SMS back
<b>Seam</b>	Stitched (external)
<b>Color</b>	White
<b>Sizes</b>	SM, MD, LG, XL, 2X, 3X
<b>Quantity/Box</b>	100 per box, individually packed.

### FEATURES

- Certified according to Regulation (EU) 2016/425
- Chemical protective clothing, Category III, Type 5 and 6
- Antistatic treatment (EN 1149-5) - on inside
- Stitched external seams for enhanced protection against penetration from the outside to the inside of the garment
- Tyvek® zipper and zipper flap for enhanced protection

### SIZETABLE

PRODUCT SIZE	ARTICLE NUMBER	ADDITIONAL INFO
S	D14809606	
M	D14809610	
L	D14809622	
XL	D14809637	
2X	D14809645	
3X	D14809658	

### PHYSICAL PROPERTIES

PROPERTY	TEST METHOD	TYPICAL RESULT	EN
Abrasion Resistance <sup>7</sup>	EN 530 Method 2	>100 cycles	2/6 <sup>1</sup>
Basis Weight	DIN EN ISO 536	41.5/43 g/m <sup>2</sup> <sup>5</sup>	N/A
Colour	N/A	White	N/A
Exposure to high Temperature	N/A	Melting point ~135 °C	N/A
Flex Cracking Resistance <sup>7</sup>	EN ISO 7854 Method B	>100000 cycles	6/6 <sup>1</sup>
Flex Cracking Resistance at -30°C	EN ISO 7854 Method B	>4000 cycles	N/A
Puncture Resistance	EN 863	>5 N	1/6 <sup>1</sup>
Resistance to water penetration	DIN EN 20811	>10/3 kPa <sup>5</sup>	N/A
Surface Resistance at RH 25%, inside <sup>7</sup>	EN 1149-1	< 2,5 · 10 <sup>9</sup> Ohm	N/A
Surface Resistance at RH 25%, outside <sup>7</sup>	EN 1149-1	< 2,5 · 10 <sup>9</sup> Ohm	N/A

## TECHNICAL DATA SHEET

PROPERTY	TEST METHOD	TYPICAL RESULT	EN
Tensile Strength (MD)	DIN EN ISO 13934-1	>30 N	1/6 <sup>1</sup>
Tensile Strength (XD)	DIN EN ISO 13934-1	>30 N	1/6 <sup>1</sup>
Thickness	DIN EN ISO 534	140/- μm <sup>5</sup>	N/A
Trapezoidal Tear Resistance (MD)	EN ISO 9073-4	>10 N	1/6 <sup>1</sup>
Trapezoidal Tear Resistance (XD)	EN ISO 9073-4	>10 N	1/6 <sup>1</sup>

1 According to EN 14325 | 2 According to EN 14126 | 3 According to EN 1073-2 | 4 According to EN 14116 | 12 According to EN 11612 | 5 Front Tyvek® / Back |  
 6 Based on test according to ASTM D-572 | 7 See Instructions for Use for further information, limitations and warnings | > Larger than | < Smaller than |  
 N/A Not Applicable | STD DEV Standard Deviation |

## GARMENT PERFORMANCE

PROPERTY	TEST METHOD	TYPICAL RESULT	EN
Nominal protection factor <sup>7</sup>	EN 1073-2	>5	1/3 <sup>3</sup>
Seam Strength	EN ISO 13935-2	>50 N	2/6 <sup>1</sup>
Shelf Life <sup>7</sup>	N/A	10 years <sup>6</sup>	N/A
Type 5: Inward Leakage of Airborne Solid Particulates	EN ISO 13982-2	Pass	N/A
Type 6: Resistance to Penetration by Liquids (Low Level Spray Test)	EN ISO 17491-4, Method A	Pass	N/A

1 According to EN 14325 | 3 According to EN 1073-2 | 12 According to EN 11612 | 13 According to EN 11611 | 5 Front Tyvek® / Back |  
 6 Based on test according to ASTM D-572 | 7 See Instructions for Use for further information, limitations and warnings |  
 11 Based on the average of 10 suits, 3 activities, 3 probes | > Larger than | < Smaller than | N/A Not Applicable | \* Based on lowest single value |

## COMFORT

PROPERTY	TEST METHOD	TYPICAL RESULT	EN
Air Permeability (Gurley method)	ISO 5636-5	Yes/- <sup>5</sup>	N/A
Air Permeability (Gurley method)	ISO 5636-5	< 45 /- s <sup>5</sup>	N/A
Thermal Resistance, Rct	EN 31092/ISO 11092	16.3*10 <sup>-3</sup> /- m <sup>2</sup> *K/W <sup>5</sup>	N/A
Thermal Resistance, clo value	EN 31092/ISO 11092	0.105/- clo <sup>5</sup>	N/A
Water Vapour Resistance, Ret	EN 31092/ISO 11092	11.3/- m <sup>2</sup> *Pa/W <sup>5</sup>	N/A

2 According to EN 14126 | 5 Front Tyvek® / Back | > Larger than | < Smaller than | N/A Not Applicable |

## PENETRATION AND REPELLENCY

PROPERTY	TEST METHOD	TYPICAL RESULT	EN
Repellency to Liquids, Sodium Hydroxide (10%)	EN ISO 6530	>90 %	2/3 <sup>1</sup>
Repellency to Liquids, Sulphuric Acid (30%)	EN ISO 6530	>95 %	3/3 <sup>1</sup>
Resistance to Penetration by Liquids, Sodium Hydroxide (10%)	EN ISO 6530	<1 %	3/3 <sup>1</sup>
Resistance to Penetration by Liquids, Sulphuric Acid (30%)	EN ISO 6530	<1 %	3/3 <sup>1</sup>

1 According to EN 14325 | > Larger than | < Smaller than |

## CLEANLINESS

PROPERTY	TEST METHOD	TYPICAL RESULT	EN
Dry Linting Propensity, inside	BS 6909	128/- Average particle count/17 liters of air <sup>5</sup>	N/A
Dry Linting Propensity, outside	BS 6909	56/- Average particle count/17 liters of air <sup>5</sup>	N/A

5 Front Tyvek® / Back | > Larger than | < Smaller than | N/A Not Applicable | STD DEV Standard Deviation |

### WARNING

Although the Tyvek® fabric itself may offer a barrier to a certain range of low concentrated inorganic chemicals, the fabric is no barrier to liquids under pressure. In case you need a barrier to liquids under pressure, please take a chemical protective clothing category III type 3, such as Tychem® C or F into consideration. The garment does not protect against ionizing radiation.

The information provided herein corresponds to our knowledge on the subject at the date of its publication. This information may be subject to revision as new knowledge and experience becomes available. The data provided fall within the normal range of product properties and relate only to the specific material designated; these data may not be valid for such material used in combination with any other materials or additives or in any process, unless expressly indicated otherwise. The data provided should not be used to establish specification limits or used alone as the basis of design; they are not intended to substitute for any testing you may need to conduct to determine for yourself the suitability of a specific material for your particular purposes. Since DuPont cannot anticipate all variations in actual end-use conditions DuPont makes no warranties and assumes no liability in connection with any use of this information. Nothing in this publication is to be considered as a license to operate under or a recommendation to infringe any patent rights.

This garment and/or fabric are not flame resistant and should not be used around heat, open flame, sparks or in potentially flammable environments.

### DuPont™ SafeSPEC™ - We're here to help

Our powerful web-based tool can assist you with finding the appropriate DuPont garments for chemical, controlled environment, thermal and mechanical hazards.



**DuPont Personal Protection  
SafeSPEC™**

 [DuPont Personal Protection](#)

 [@DuPontPPE](#)

 [DuPont Personal Protection](#)

**CREATED ON: JULY 4, 2022**

© 2022 DuPont. All rights reserved. DuPont™, the DuPont Oval Logo, and all trademarks and service marks denoted with ™, SM or ® are owned by affiliates of DuPont de Nemours, Inc. unless otherwise noted.